

Technical Specifications: **EXPO** (article code: 117)

| | Unity measurements | Values and tolerances (*) |
|--------------------------------|--------------------|---------------------------------|
| Fiber Composition | % | 100% PROPITEX FR bacteriostatic |
| Roll width | cm | 140 ± 2 |
| Weight per square meter | g/mq | 300 ± 15 |

| | Values and tolerances (*) | |
|---|----------------------------|-----|
| Abrasion Resistance | > 100000 Martindale cycles | |
| Light Fastness (EN ISO 105-B02) | 5 | |
| | Wet | Dry |
| Fastness to Rubbing (EN ISO 105-X12) | 5 | 5 |

| | |
|---------------------|--|
| Flammability | 1 IM UNI 9175 EN 1021-1:2006 EN 1021-2:2006 BS5852:2006 (CRIB5) California Technical Bulletin 117:2013 M1 |
|---------------------|--|

Maintenance symbols (**)



DECLARATION OF CONFORMITY

Does not hold Formic Aldehyde (Formaldehyde) standard UNI 8647
 Reference to art. 1 par. 2 Decree 15/07/94 of the German Board of Health and its subsequent modifications; i.e. it does not contain azoic dyes that in reducing conditions develop amines (Law 28/07/94 n. 1670 - VERORDNUNG BGBL).
 Content of heavy metals in the dyes within the tolerance limits (OEKO TEX STANDARD 100).
 DPR 883 - fibrous composition (code). Legislative Decree 22/05/99 n. 194 - Official Gazette n° 146 of 24/06/99.

(*) Tolerances suggested by the Technical Committee of A.E.I.H. (European Association of Garment Manufacturing Companies)

(**) In reference Italian Law n.126 (1991 – article 2), is necessary indicate to the consumer, limitation and particular caution to follow for normal use of the product.