

Test Report No. BTX 32004(1)/PS/06

Date: 11 February 2006

Page 1 of 2

Fidivi Tessitura Vergnano Spa
Via Le Fiume 3
10023 Chieri (TO)
United Kingdom

Attention: Giuseppe Prestigiacomo

The following sample was submitted and identified by the client as:

<u>Sample Description:</u>	Upholstery fabric, Ref: BONDAI
<u>Details of Sample:</u>	100% polyester
<u>Date Sample(s) Received:</u>	17 January 2006
<u>Testing Period:</u>	Tested between 17/01/06 and 01/02/06
<u>Test(s) Requested:</u>	BS EN 1021-1/2:1994
<u>Test Results:</u>	Detailed in Appendix A
<u>Comments/Conclusions:</u>	The composite tested complies with the requirements of BS EN 1021-1/2:1994.

Signed for and on behalf of
SGS United Kingdom Ltd



Paula Smith
Textile Technologist
Softlines Department

"This document is issued by the Company subject to its General Conditions of Service available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated: (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company."

Tests denoted with an * have been subcontracted to another UKAS Approved Laboratory. Tests marked [Non UKAS Accredited] in this Report/Certificate are not included in the UKAS Accredited Schedule for our Laboratory

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation

Appendix A: Test Results

Furniture-Assessment of the ignitability of upholstered furniture (BS EN 1021-1/2: 1994)

Part 1-Smouldering cigarette and Part 2-Match flame equivalent

The sample was tested in accordance with BS EN 1021-1/2:1994

Water soaking Procedure (BS EN 1021-1:1994)

The sample was tested after the water soaking procedure as specified in BS EN 1021-1:1994 Clause 7.1

Filling material used:

The foam filling was supplied by the customer and is described as a combustion modified foam infill of approximate density 35 kg/cu.m.

The following results relate only to the ignitability of the combinations of materials, under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source- smouldering cigarette (BSEN1021-1:1994)

No flaming or smoking, and no progressive smouldering was observed within 60 minutes after the placement of the cigarettes PASS

Ignition Source- Match-equivalent butane flame (BSEN1021-2:1994)

Flaming ceased within the 2 minutes of the removal of the ignition source and no progressive smouldering was observed 60 minutes from the removal of the ignition source. PASS

***** End of Report*****